GLAVA® MARINE ROLL/SLAB 16 Product information



Material:	Mineral wool				
Density (t=100mm):	Approx. 17,5 kg/m ³ (±1,5 kg/m3)				
Thermal conductivity:	λ ₁₀ =0,034 W/mK				
Width:	570 - 1200 mm				
Length:	1200 mm →				
Thickness:	Various				

Product properties

Fire safety:	Classified as a non-combustible material, acc. to IMO FTPC Part 1
Humidity:	Do not expose the product to water, either before, during or after construction
Dimensional stability:	Glava products will keep their dimensional stability and will not alter or subside with time
Radon:	Mineral wool is one of the materials with lowest radon radiation; any risk excluded
Allergy:	It is not likely that allergies will develop when working with mineral wool
Thermal conductivity:	See table. Acc.to EN 12667

Medium temp. [°C]	-160	-80	-40	-10	+20	+50	+100	+150	+200
thermal conductivity [W/mK]	0,011	0,021	0,027	0,031	0,035	0,041	0,053	0,068	0,085

Product Description

- Mineral wool to be used as thermal and acoustic insulation in wessels, offshore units and industry applications.
- Cutting tool: knife
- For thermal insulation of coolers, freezercompartments and hot water heaters
- Heat and fire resisting mineral wool
- Accordance to DNV's "Rules for classification of ships and mobile offshore units" - (DNV nr. MEDB00000DD)
- CE-Mark: DoP N0002-CPR-008

Quality Assurance

Glava has *NS-EN ISO 9001* and *NS-EN ISO 14001* – certificates from NCS (Nemko Certification system AS) This ensures high and uniform quality of our products.

Glavas product range is under a constant running development. Glava reserve the right to revise products and product specification without notice. A Health and Safe Handling data sheet is available on our Internet pages.



GLAVA AS, P.O Box 2006, N-1801 ASKIM, Norway Telephone: +47 69 81 84 00 Fax: +47 69 81 84 78 www. glava.no