

## Sanitary Silicone Premium DSSA

Properties	Value	Unit	Method / Remarks
Uncured Rubber:			
Crosslinking System	acetoxo		
Tack Free Time	5	min	23 °C, 50 % RH
Density	1,05	g/ml	
Consistency	non-sag		
Curing Speed	4	mm/d	23 °C, 50 % RH
Application Temperature	+5 to +35	°C	
Shelf Life	18	months	
Cured Rubber:			
Elongation at Break	> 350	%	NFT 85 507
Stress at 100 % Elongation	0,35	N/mm <sup>2</sup>	ISO 37
Hardness, Shore A	17		ISO 868
Shrinkage	none	%	ISO 10563
Temperature Resistance	-50 to +200	°C	
Slump	none	%	ISO 7390
Standards	ISO 11600 F & G, Class 25		

### Product Details

Sanitary Silicone Premium DSSA is a one-part, acid-curing silicone sealant for general-purpose sealing and for sanitary applications. The sealant features rapid cross-linking, excellent tooling properties and has fungicidal properties.

### Direction for use

The substrate areas that will be in contact with the sealant must be clean, dry, and free of all loose material, dust, dirt, rust, oil and other contaminants. Non-porous substrates should be cleaned with a solvent and a clean, white, lint-free, cotton cloth. Wipe dry immediately with another such cloth before the solvent evaporates from the surface.

Sanitary Silicone Premium DSSA exhibits excellent primer less adhesion to most materials used for sanitary application, e.g. glass, tiles, ceramics, enamel, glazed tiles and clinker; plastics, e.g. epoxide, polyester, polyacrylate. Preliminary compatibility tests are recommended on unusual substrates.

Sanitary Silicone Premium DSSA should not be used on substrates such as marble, concrete, fibrous cement and mortar, as the product releases acetic acid during vulcanization. It should not be used in contact with metals such as lead, copper, brass or zinc due to corrosion. The sealant may be discolored in contact with some elastomers, e.g. EPDM and neoprene.

For further safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

The information in this adhesives brochure and our application-technology consulting, verbally and in writing, is given to the best of our knowledge, but is non-binding and is not a guarantee in the sense of § 443 BGB. We recommend that, before using our products, you check the suitability for the intended application. As the individual product can be used for a wide range of applications and the conditions on site that cannot be estimated, we also recommend testing the bonding before using the product.