



WOOD

Epoque  
Miniplank



Product  
Datasheet  
2012

WOOD

# Epoque Miniplank




TECHNICAL INFORMATION	EPOQUE
Thickness	14 mm
Width	117
Length	1075/1245
Wearlayer thickness (mm)	app. 3,6
Weight (kg/m <sup>2</sup> )	app. 8,0
Taber Abraser/Lacquer's wear resistance* prEN 13696	
abrasion penetration Proteco Lacq.(revs)	>4000
abrasion penetration Proteco Nat.(revs)	>3500
abrasive wear (mg/100revs)	app. 3,5
Reduction of sound weighted index index "footfall" to the room below. NF EN ISO 140-8 / Acc to NF EN ISO 717-2, ΔL <sub>w</sub> in dB with 2 mm Tarkofoam/flex II	17
Formaldehyde emission EN 13986	E1
Reaction to Fire EN 13501	D <sub>f1</sub>
Thermal insulation value (RT m <sup>2</sup> K/W)	
board only	0,101
with rag felt	0,121
with 2 mm Tarkofoam/flex II	0,141
Installation**	Floating /Glue down
Underfloor heating compatible***	Maximum floor surface temperature 27°C with self-regulating under-floor heat system.

\* Data show results with new components according to 2006 update.  
Method not applicable for stained, brushed or hardwax oiled products.

\*\* Contact your flooring supplier for further information.

\*\*\* Not suitable for the woodspecies beech and maple.

Epoque Proteco Lacquer / Proteco Natura



EPOQUE	Lacquer 2-lock l: 1245mm	Natura 2-lock l: 1245mm	Lacquer 2-lock l: 1075mm	Natura 2-lock l: 1075mm
<b>Miniplank, 14x117 mm. Minibevél lengthwise.</b>				
Oak Nature	•	•	•	
Oak Nature brushed	•			
Oak Rustic brushed	•	•		
Oak White		•		•
Oak Java Gold brushed		•		•
Oak Cotton White		•		
Oak Patina White brushed		•		
Oak Stone Grey brushed		•		
Oak Praline brushed		•		
Beech Steamed	•		•	
Merbau	•		•	
Jatoba	•		•	

Wood floors, Brinell Hardness (BHN), EN1534

