

Omnisports REFERENCE



KEY POINTS

Description :

Vinyl sports floor covering over fibreglass mat with PVC foam backing. Sanitized® (anti-bacterial coating). Protected with Top Clean XP® (dirty-resistant treatment for ease of maintenance)

3 types of installation :

- Loose laid
- Glued Installation
- Installation on Tarkolay

Surface Texture : Sorrent

Compatible Installation :

Association possible with a sub construction (Lumaflex type)

Installation instructions and maintenance guide :

On request

Dimensions (EN 426/EN 427) :



2 m



20.5 m or 23 m

Total thickness (EN 428/EN429):



6.5 mm (± 0,15mm)

Total weight (EN 430) :























4.71 kg/sqm (± 500g)

| Properties | Standards | Omnisports REFERENCE | | |
|------------|-----------|----------------------|--------------------|--------------------------|
| | | Loose-laid | Glued Installation | Installation on Tarkolay |






| Sports properties | | | | |
|-----------------------|-------------|---------|---------|---------|
| Friction | EN 13036-4 | 88 | | |
| Shock absorption % | EN 14 808 | 26 | 27 | 28 |
| Vertical deformation | EN 14 809 | 1.11 mm | 1.33 mm | 1.26 mm |
| Vertical ball rebound | EN 12235 | 100 % | 99 % | 100 % |
| Specular gloss | EN ISO 2813 | 14.4 % | | |

| Classification | | |
|-----------------------|------------|----------------------------------|
| Reaction to fire | EN 13501-1 | Cfl-S1 |
| | | On raw concrete and wooden board |
| Formaldehyde Emission | EN 717-1 | No formaldehyde |
| | EN 717-2 | |
| Pentachlorophenol | EN 12673 | No pentachlorophenol |

| Technical Characteristics | | | |
|--------------------------------|---------------|----------------|---------|
| Wear Layer | EN 429 | 0.70 mm | |
| Abrasion | EN ISO 5470-1 | 0.098 g | |
| Resistance to indentation | EN 1516 | 0.21 mm | 0.40 mm |
| Behaviour under a rolling load | EN 1569 | ≤ 0.50 mm | |
| | | No degradation | |
| Resistance to impact | EN 1517 | No degradation | |

| Specific Characteristics | | | | |
|---|---|--|---|---|
| Surface treatment | Anti bacteria and anti fungus treatment + Topclean X-treme performance protection | | |   |
| Maintenance |  |  |  |  |
| Available Colours 10 plain colours 4 wood looks |  |  |  |  |
| |  |  |  |  |
| |  |  | | |
| |  |  |  |  |

COMPATIBLE SLABS: Concrete, asphalt screed, anhydrite screed. Any deviation of the slab must be corrected prior installation (6 mm under a 3 m straight edge). We reserve the right to modify these specifications without, however, affecting their compliance with standards.

| | | |
|--|--|--|
|  09 | EN 14904 : 2006 Vinyl Indoor sport floor with PVC foam backing | Manufactured in: Tarkett Sedan SAS 2 avenue François Sommer 08200 SEDAN FRANCE EN 651 OMNISPORTS REFERENCE |
| |  On raw concrete and wooden board  26% loose laid  27% glued installation  28% installation on Tarkolay | |

| | | | |
|---|---|---|---|
| The Sedan production factory is registered and conforms to the ISO 9001:2000 quality management system. |  | The Sedan production factory is registered and conforms to the environmental management system ISO 14001. |  |
|---|---|---|---|



| | |
|---------|------------------|
| 43,5 % | 100 % |
| Natural | 19 % |
| | Recyclable |
| | Recycled content |



On loose laid only

Tarkett France – 2, rue de l'Égalité – 92748 Nanterre cedex – TÉL. +33(0)1 41 20 40 40 – FAX +33(0)1 41 20 47 05 – info@tarkett.com
 S.A.S au capital de 30800000 euros – RCS Nanterre 410 081640

www.tarkett-sports.com



THE ULTIMATE SURFACE EXPERIENCE

V1 30/04/2011