

## General data

Panel: 1 strip/ 3 strip	1820 x 145 mm/1820 x 190 mm
Total thickness	12,5 mm
Numbers of panels per pack	6
m <sup>2</sup> per pack: 1 strip / 3 strip	1,5834 m <sup>2</sup> / 2,0748 m <sup>2</sup>

## Panel build up

Toplayer	PEFC controlled sources	EN 13489	2,5 mm
Core board	PEFC controlled sources		HDF
Backing layer	PEFC controlled sources	Spruce or Pine	2 mm
Tongue and groove	Length		Uniclic
	Width		Uniclic Multifit

## Surface layer

Wood species	Oak
Origine	Europe
Finishing	cf catalogue/website
Grading	cf catalogue/website

## Installation

		Norm requirements	Magnum values
Floating	On Magnum underlay	CF installation instructions	
Glued to subfloor	Magnum MS polymer resin	CF installation instructions	
General aspect of installed flooring	EN 13489	Lipping - difference in height (mm)	≤ 0,20
		difference in width (mm)	≤ 0,20
		cupping lengthwise %	≤ 0,1
		cupping in width %	≤ 0,2
Dimensional stability	ISO 24339 Changes 30 - 85 % RH	Cupping short side max %	≤ 0,30
		Cupping short side min %	≥ - 0,20
		Open joints short side (mm)	≤ 0,20
		Open joints long side (mm)	≤ 0,30

## Warranty

Domestic use	Conditions in each pack	25 years
Uniclic connection		Lifetime
Commercial		On request

## Finishing

UV cured varnish	Anti-scratch top coat	5 - 7 layers	
Wear resistance	SIS 923509	Falling sand	800 - 1000
	DIN 68861	S 33	100 - 1050
Stain resistance	EN 13442	All except blue ink	class 5
		Blue ink	class 3
CE	EN 14342: 2008-09	notified body	0766 EPH Dresden
Castor chairs	Use soft castors, type W (EN 12529) and/or suitable office mat		
Slip resistance	CEN/TS 15676 : 2008		USRV 48-52
Emission of formaldehyde	EN 717-1		E1
PCP			below detection limit
Heat resistance	EN 12664: 2001		0,11 m <sup>2</sup> .K/W
Underfloor heating	Suitable	CF special installation instructions	
Reaction to fire	EN 14501-1		Cfl-s1

## Ecological certificates

U-zeichen	Z.156.606-898
AFFSET	A
PEFC	PEFC/07-32-37
EPD	On request



EN14342:2013  
Wood Floor - Multi layer  
Parquet EN 13489

