

**Tregulv**  
**Flersjiktsparkett**

Wood flooring  
Multi-layer parquet elements

Table 1 — Classification for *Quercus* spp. (oak)

Face of the element				
Features	Class			
	○	△	□	
<b>Sound sapwood</b>	Not permitted	Permitted up to 50 % of the face, if distributed	All features permitted without limit to size or quantity if these do not impair the strength or the wearing quality of the parquet flooring.	
<b>Knots</b> <sup>a</sup> Sound and intergrown Unsound knots	Permitted if: diameter ≤ 3 mm diameter ≤ 1 mm if not grouped together <sup>b</sup>	Permitted if: diameter ≤ 8 mm diameter ≤ 2 mm		
<b>Checks</b>	Not permitted	Permitted up to 20 mm in length per strip		
<b>Bark pockets</b>	Not permitted	Not permitted		
<b>Lightning shake</b>	Not permitted	Not permitted		
<b>Slope of grain</b>	Permitted, no limit	Permitted, no limit		
<b>Colour variation</b>	Slight variation permitted	Permitted		
<b>Medullary ray</b>	Permitted	Permitted		
<b>Biodeterioration</b>	Not permitted	Not permitted		Not permitted, except blue stain and black holes.
<b>Non-visible parts</b>				
All features permitted without limit to size or quantity if these do not impair the strength or the wearing quality of the parquet flooring.				
<sup>a</sup> Cracks in knots and knot holes shall be filled.				
<sup>b</sup> Knots are grouped together if the distance separating them, measured from edge to edge, does not exceed 30 mm.				