

Tikkurila Sverige AB
Elisabet Wallgren
Textilgatan 31
120 86 STOCKHOLM

Emission measurement according to M1

(3 appendices)

Assignment

At the request of Tikkurila Sverige AB an emission measurement regarding VOC according to “M1 Emission Classification of Building Materials: Protocol for Chemical and Sensory Testing of Building Materials”, ver 21.5.2014, has been carried out.

The measurements are made after 28 days of conditioning regarding volatile organic compounds, carcinogenic compounds (EU Regulation No 1272/2008 Annex VI, cat 1A and 1B), formaldehyde, ammonia and sensory acceptability.

Product/test specimen

Product type:	Interior paint
Product name:	Beckers Støvbinders hvit
Batch No:	B7189558
Manufacturing date:	2014-04-04
Packaging:	Tin can, 1 L
Arrived at SP:	2014-05-07
Test specimen preparation:	The product can be used both on ceiling and walls. Wall scenario is used for the testing. Chemical testing: The paint was applied with a roller on a glass plate of 0.20 x 0.20 m. Applied amount was 11.8 g (= 296 g/m ² = 5 m ² /L). Sensory testing: Twelve glass plates of 0.25 x 0.57 m were applied with a roller. Mean applied amount per plate was 42 g (= 296 g/m ² = 5 m ² /L). The product can be used both on ceiling and walls. Wall scenario is used for the sensory testing.
Deviation from protocol:	No deviations.
Test period started, date:	2014-05-08 (chemical), 2014-07-17 (sensory)
Conditions during ageing:	23 ± 2 °C, 50 ± 5 % RH
Emission samplings, date:	2014-06-05 (chemical), 2014-08-15 (sensory)

SP Technical Research Institute of Sweden

Postal address
SP
Box 857
SE-501 15 BORÅS
Sweden

Office location
Västeråsen
Brinellgatan 4
SE-504 62 BORÅS

Phone / Fax / E-mail
+46 10 516 50 00
+46 33 13 55 02
info@sp.se

Laboratories are accredited by the Swedish Board for Accreditation and Conformity Assessment (SWEDAC) under the terms of Swedish legislation. This report may not be reproduced other than in full, except with the prior written approval of the issuing laboratory.

Methods

The specimens were conditioned outside the testing chambers in a controlled climate conditions of 23 ± 2 °C and 50 ± 5 % RH. The specimens were placed in the chambers three (chemical) and two (sensory) days before the measurements.

Chamber conditions of the test of chemical emissions:

Test chamber volume:	0.03 m ³ , stainless steel
Temperature:	23 ± 1 °C
Relative Humidity:	50 ± 3 % RH
Air exchange rate:	1.5 h ⁻¹
Air velocity at specimen surface:	0.1 – 0.3 m/s
Area of sample:	0.04 m ²
Area specific air flow rate:	1.1 m ³ /m ² h

Chamber conditions of the test of sensory acceptability:

Test chamber volume:	1.0 m ³ , stainless steel
Temperature:	23 ± 1 °C
Relative Humidity:	50 ± 3 % RH
Supply air flow rate:	0.9 l/s = 3.24 m ³ /h
Area of sample:	1.7 m ²

Emission sampling and analytical methods:

Test	Sampling method	Adsorbent	Sampling volume (litre)	Analysis method / Quantification	Detection limit
VOC	SP 1314 ¹	Tenax TA	3 - 8	SP 0601 ² / FID quantification	1 µg/m ³
Formaldehyde	SP 1314 ¹	DNPH	46	SP 2303 ³ / HPLC-UV	0.03 µg/sampler
Ammonia	SP 1314 ¹	Silica gel	190, 230	Liquid chromatograph with conductivity detector ⁴	0.9 µg/sampler
Sensory evaluation	Untrained panel of min 15 persons	--	--	--	--

¹⁾ In accordance with ISO 16000-9:2006, accredited method.

²⁾ In accordance with ISO 16000-6:2011 and M1 protocol, accredited method.

³⁾ In accordance with ISO 16000-3:2001, accredited method.

⁴⁾ The determinations of the sampled silica gel tubes were done by Sahlgrenska Universitetssjukhuset, Miljökemiska laboratoriet, Göteborg, not accredited method.

Tenax TA was used as adsorption medium for VOC. The Tenax tubes were thermally desorbed and analysed in accordance to ISO 16000-6:2011 (Determination of volatile organic compounds in indoor and test chamber air by active sampling on Tenax TA sorbent, thermal desorption and gas chromatography using MS/FID), accredited SP method 0601. This means an analysis in a gas chromatograph and detection with a flame ionisation detector (FID) and mass selective detector (MS). The FID signals are used for compound quantification. The TVOC is quantified as toluene equivalents. The mass selective detector is used for identification of compounds. The capillary column used is coated with 5% phenyl/ 95 % methylpolysiloxane.

Tenax TA was also used as adsorption medium for testing of volatile carcinogenic compounds, according to EU Regulation No 1272/2008 Annex VI, cat 1A and 1B), (exclusive formaldehyde), 0.001 mg/m³ and above. The compound specific response factors were calculated.

The sampling of formaldehyde was carried out with DNPH samplers. The samplers were analysed according to ISO 16000-3 (in accordance to accredited SP method 2302), which means analysis on a liquid chromatograph with absorbance detector.

The sampling of ammonium was carried out with silicagel treated adsorbent tubes and analysis on a liquid chromatograph with conductivity detector.

Two subsequent samples were taken for the VOC determination, for the formaldehyde and for the ammonia respectively.

Results

The results of the chemical testing are expressed as concentrations in the model room and as area specific emission rates:

A model room has a volume of 30 m³ and an air change rate of 0.5 changes per hour. The concentration of VOC in the model room can be calculated according to this equation:

$$Conc = \frac{SER_A \times A}{n \times V}$$

Conc = concentration of a VOC in the model room, in µg/m³
 SER_a = area specific emission rate, in µg/m²h
 A = area of sample, in m² (31.4 m² for walls)
 n = air exchange rate, in changes per hour
 V = volume of the model room, in m³

Results of the chemical testing of the sample of **Beckers Støvbindet hvit** after 28 days:

Compound	Concentration in model room mg/m ³	Emission rate mg/m ² h	Criteria M1 mg/m ² h
TVOC	< 0.020	< 0.010	< 0.2
Carcinogens	< 0.002	< 0.001	< 0.005
Formaldehyde	< 0.002	< 0.001	< 0.05
Ammonia	< 0.010	< 0.005	< 0.03

Test report from Sahlgrenska Universitetssjukhuset: test report 2014:25 dated 2014-06-25.

See appendix 1 for gas chromatogram from the VOC determination.

Results of the sensory evaluation of the sample of **Beckers Støvbindet hvit** after 28 days:

Evaluator	Sensory evaluation	Criteria M1
1	0.95	$\geq + 0.0$
2	0.55	
3	0.60	
4	0.70	
5	0.50	
6	0.95	
7	0.95	
8	0.85	
9	0.90	
10	0.50	
11	0.95	
12	0.20	
13	0.25	
14	0.75	
15	0.90	
Arithmetic mean of acceptability:	0.7	

Standard deviation: 0.26

90 % confidence interval of arithmetic mean: 0.12

The empty sensory test chamber acceptability was determined 2014-08-13. The mean acceptability vote of the empty chamber was > 0.8 .

Interpretation of the results

The tested product **Beckers Støvbindet hvit** complies with all the requirements of M1 for the tested parameters.

Detailed results

Detailed results (emission rates) of the chemical testing after 28 days:

Sample	TVOC (mg/m ² h) as toluene equivalents between C ₆ -C ₁₆	Formaldehyde (mg/m ² h)	Ammonia (mg/m ² h)	Carcinogens (mg/m ² h) between C ₆ -C ₁₆
1	< 0.010	< 0.001	< 0.005	< 0.001
2	< 0.010	< 0.001	< 0.005	< 0.001

Single VOCs above 0.005 mg/m³ in the model room (as toluene equivalents):

Single VOCs	Retention time (min)	CAS number	Concentration (mg/m ³)	
			Sample 1	Sample 2
Single VOCs C₆-C₁₆:	5.5 – 36.8			
Possibly: Di(sec-butyl) 2-metylsuccinat	36.2	57983-31-0	0.009	0.009
		TVOC:	0.009	0.009
Single VOC outside C₆ – C₁₆:				
VVOC (< C ₆) ⁵	4.5 – 5.5			
No single VVOC detected	--	--	--	--
SVOC (C ₁₆ – C ₂₂) ⁶	36.8 - 42.0			
No single SVOC detected	--	--	--	--

⁵⁾ VVOC = very volatile organic compounds, as defined in ISO 16000-6 (not accredited)

⁶⁾ SVOC = semi-volatile organic compounds, as defined in ISO 16000-6 (not accredited)

Level of identification of compounds is 100 % for all compounds ≥ 0.005 mg/m³.

Measurements uncertainty

SER_{TVOC}: ± 15 %, SER_{Formaldehyde}: ± 30 %, SER_{NH3}: ± 14 %

**SP Technical Research Institute of Sweden
SP Chemistry, Materials and Surfaces - Chemistry**

Performed by

Maria Rådemar

Examined by

Anders Lorén

Appendices


1. Gas Chromatogram
2. Photo of test specimen
3. Sampling report

Appendix 1

Gas chromatogram

Sample: **Beckers Støvbindet hvit**, after 28 days (sampled volume: 9 litres):

Abundance




TVOC between C_6 and C_{16} , means compounds eluting between 5.5 and 36.8 minutes.

The compound with retention time 4.3 min is a contamination from the analysis system.

Appendix 2

Photo of test specimen



The specimen for the chemical testing.

Sampling Report (paints etc)

11

Sampler (Name, Company, contact info) Elisabet Wallgren RDI Interior Products Tikkurila Sverige AB elisabet.wallgren@tikkurila.com	Manufacturer of the product Tikkurila
Name of product Beckers Størbinder hvit	Product category according to EN 16402:20113, clause 5: Product category 1
Manufacturing Date 140404	Batch No B7189558
Amount of material sampled 1 liter	
Sample is taken from: Production line <input type="checkbox"/> Stock / Storage <input checked="" type="checkbox"/> Miscellaneous <input type="checkbox"/> -where, specify:	How was the product stored before sampling? At lab in room temperature
If a sub-sample was collected from a larger material amount, describe how the sub-sample was taken The paint was properly mixed and then poured into a smaller can.	Packing material: Tin can
Recommended application amount, solid content, density or other 5-8 m ² /liter $\rho = 1,48 \text{ g/cm}^3$ TH = 32,98 vol-%	
Confirmation I hereby confirm that the sample was selected, taken and packed in accordance with M1 testing protocol	
Date of sampling 2014-05-05	Signature Elisabet Wallgren