

ID 1120wp_uk	Rev. 01	Date 30/07/09	Interchar 1120	Page 1 of 18
-----------------	------------	------------------	----------------	--------------

Interchar[®] 1120 Application Guidance Notes

Prepared by:

International Paint Ltd.
www.international-pc.com

TECHNICAL AND APPLICATION DATA herein is for the purpose of establishing a general guideline of the coating and proper coating application procedure. Test performance results were obtained in a controlled laboratory environment and International makes no representation that the exhibited published test results, or any other tests, accurately represent results actually found in all field environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection, verification of performance, and use of the coating(s).

Protective Coatings

All products supplied and technical advice or recommendations given are subject to our standard Conditions of Sale.

Registered in England No. 63604
Registered Office 26th Floor, Portland House, Bressenden Place, London SW1E 5BG



ID 1120wp_uk	Rev. 01	Date 30/07/09	Interchar 1120	Page 2 of 18
-----------------	------------	------------------	----------------	--------------

Table of Contents

1.0	Introduction	3
2.0	Where to Apply Interchar 1120	4
3.0	Storage of Material	5
4.0	Environmental Conditions for Application	6
5.0	Surface Preparation	7
6.0	Primers and Overcoating	8
7.0	Topcoats	9
8.0	Airless Spray Application	10
9.0	Brush and Roller Application	11
10.0	Standard of Cosmetic Finish	12
11.0	Possible Film Defects	13
12.0	Measurement of Dry Film Thickness	14
13.0	Inspection and Repair	16
14.0	Health and Safety	18

Protective Coatings

All products supplied and technical advice or recommendations given are subject to our standard Conditions of Sale.

Registered in England No. 63604
Registered Office 26th Floor, Portland House, Bressenden Place, London SW1E 5BG



ID 1120wp_uk	Rev. 01	Date 30/07/09	Interchar 1120	Page 3 of 18
-----------------	------------	------------------	----------------	--------------

1.0 Introduction

Interchar 1120 is a single pack water-borne intumescent coating designed to provide 60 to 120 minutes fire protection to structural steelwork in internal environments.

Interchar 1120 is tested and approved to BS476 Parts 20-22:1987 and third party confirmed through the Warrington Certification Ltd "Certifire" scheme.

This document gives detailed guidance on the use and application of Interchar 1120 and should be read in conjunction with the Technical Datasheet and Material Safety Datasheet (MSDS).

Reference throughout this procedure is made to the UK document Structural Fire Design: Off-Site Applied Thin Film Intumescent Coatings (ref. SCI P160, Second Edition), from the Steel Construction Institute. Other measuring schedules and acceptance criteria are in use, for example the AWCI (Association of Wall and Ceiling Industries) Technical Manual 12-B.

Protective Coatings

All products supplied and technical advice or recommendations given are subject to our standard Conditions of Sale.

Registered in England No. 63604
Registered Office 26th Floor, Portland House, Bressenden Place, London SW1E 5BG



ID 1120wp_uk	Rev. 01	Date 30/07/09	Interchar 1120	Page 4 of 18
-----------------	------------	------------------	----------------	--------------

2.0 Where To Apply Interchar 1120

Interchar 1120 can be used in on-site application situations to provide fire protection on structural steel sections such as universal beams, columns and hollow sections.

In all cases, specific country approvals may be required. Consult International Protective Coatings for the latest information.

Interchar 1120 can be specified for internal environments such as those described in ISO12944 C1 to C3 corrosivity categories.

Interchar 1120 can be used over a range of approved priming systems and overcoated with a range of approved top coats (refer to section 6 more details). Only approved primers and topcoats should be used; for use of other primers and topcoats, please contact International Protective Coatings for assistance.

An Interchar 1120 fire protection specification typically requires the following:

Surface Preparation	To provide optimum adhesion for the primer and Interchar 1120 to the substrate to ensure sufficient adhesion for the developing char under a fire scenario.
Priming System	To provide anti-corrosive protection to the steelwork, Interchar 1120 must always be applied to a suitably primed steel substrate.
Interchar Product	<p>In a fire scenario, the intumescent coating reacts to heat by rapidly swelling to produce a carbonaceous char which acts as an insulating layer between the steelwork and the elevated temperature of the environment.</p> <p>The dry film thickness of the Interchar product to be applied will vary depending on the size and configuration of the individual steel sections along with the desired period of fire protection required. Dry film thickness figures for all Interchar products are available from International Protective Coatings.</p>
Top Coat	Also known as sealer coats or finish coats to protect Interchar 1120 from moisture, provide a decorative cosmetic finish, and reduce dirt and dust retention.

ID 1120wp_uk	Rev. 01	Date 30/07/09	Interchar 1120	Page 5 of 18
-----------------	------------	------------------	----------------	--------------

3.0 Storage Of Materials

Interchar 1120 should be stored in dry, shaded conditions and must be protected from freezing at all times during storage and transport. The recommended storage temperature is between 4°C (39°F) and 25°C (77°F). To facilitate airless spray application characteristics, Interchar 1120 should be stored in a warm environment (15°C (59°F) to 25°C (77°F)) for at least 16 hours prior to commencement of spraying.

The shelf life of Interchar 1120 at 25°C is 6 months from date of manufacture, subject to re-inspection thereafter. Containers should remain unopened until needed and used in date order. Shelf life may be reduced at higher storage temperatures.

ID 1120wp_uk	Rev. 01	Date 30/07/09	Interchar 1120	Page 6 of 18
-----------------	------------	------------------	----------------	--------------

4.0 Environmental Conditions For Application

Interchar 1120 should be applied at air and substrate temperatures between 10°C and 40°C (50–104°F). The surface must be dry and the surface temperature must always be a minimum of 3°C (5°F) above the dew point. In line with good painting practice, application should not take place in conditions which are deteriorating, e.g. where the temperature is falling and is likely to go below 10°C (50°F) or where there is a risk of condensation forming on the steel.

For optimum application and drying, the air and substrate temperature should be greater than 10°C (50°F) and relative humidity less than 80%. Application at temperatures below 10° (50°F) and at higher humidities will retard drying and could compromise the ultimate coating performance.

Air movement is the most significant factor affecting the drying of water-borne paints. Good air flow and ventilation are always recommended to ensure there are no areas around the structure with no ventilation. With little air movement, it is possible that an increase in the local relative humidity will soon reach unacceptable levels, resulting in extended drying/overcoating times and poor performance. Forced ventilation such as the use of portable fans in direct contact with freshly applied Interchar 1120 is not recommended as it can lead to surface defects, for example skinning or wrinkling.

Interchar 1120 must be protected from condensation and water during application and drying.

Un-topcoated Interchar Systems

Interchar 1120 systems without a topcoat may only be applied and exposed where there is NO possibility of water and chemical exposure - i.e. Interchar 1120 must always be protected from pooling or running water, driving rain, high humidity/condensation, chemical or biological attack, etc.

Topcoated Interchar Systems

Top-coated systems are resistant to general atmospheric conditions up to and including C3 internal environments, as described in ISO 12944. However Interchar 1120 systems must not be exposed to pooling water or immersion/water soaking.

If in doubt, please consult International Protective Coatings.

ID 1120wp_uk	Rev. 01	Date 30/07/09	Interchar 1120	Page 7 of 18
-----------------	------------	------------------	----------------	--------------

5.0 Surface Preparation

Correct surface preparation is the foundation for success of any coating application and intumescent systems are no exception.

All surfaces to be coated should be clean, dry and free from contamination including dirt, salts, oil and grease and should be assessed and treated in accordance with ISO 8504:1992. Where necessary, remove weld spatter and smooth weld seams and sharp edges.

Interchar 1120 must always be applied over an approved anti-corrosive primer system, which has been applied to an abrasive blast cleaned steel substrate (Sa2½ (ISO 8501-1:2007) or SSPC-SP6).

Primed Surfaces

The primer surface should be dry and free from all contamination and Interchar 1120 must be applied within the overcoating intervals specified (consult the relevant primer product data sheet). The primer must have been applied to a steel surface that has been prepared in accordance with the bare steel requirements as above

Areas of breakdown, damage etc., should be prepared to the specified standard (e.g. Sa2½ (ISO 8501-1:1988) or SSPC SP6, Abrasive Blasting, or SSPC SP11, Power Tool Cleaning (for small areas) and patch primed prior to the application of the Interchar product.

Should the primer's suitability for overcoating be in doubt in any way, for example, primer type unknown, primer not approved, excessive dry film thickness, surface contamination, surface glossiness etc, International Protective Coatings MUST be consulted prior to the application of any Interchar product.

Protective Coatings

All products supplied and technical advice or recommendations given are subject to our standard Conditions of Sale.

Registered in England No. 63604
Registered Office 26th Floor, Portland House, Bressenden Place, London SW1E 5BG



ID 1120wp_uk	Rev. 01	Date 30/07/09	Interchar 1120	Page 8 of 18
-----------------	------------	------------------	----------------	--------------

6.0 Primers & Overcoating

Interchar 1120 must ALWAYS be applied over an approved priming system which will provide the required anti-corrosive protection to the steelwork over the lifetime of the structure it is protecting. It is not designed to give anti-corrosive protection alone and is therefore NEVER applied directly to steel substrates.

Interchar 1120 has been tested as part of a coating system for use in fire situations. A list of the approved primers can be found on the latest version of the Interchar 1120 Product Technical Data Sheet. International Protective Coatings can advise on other suitable primers.

Typical primer dry film thickness recommended is between 40 and 75 microns (1.5 – 3 mils) depending upon primer product.

The maximum recommended average dry film thickness for the priming system is 150 microns (6 mils). If in doubt contact International Protective Coatings.

ID 1120wp_uk	Rev. 01	Date 30/07/09	Interchar 1120	Page 9 of 18
-----------------	------------	------------------	----------------	--------------

7.0 Topcoats

For the purposes of this document, topcoats are also referred to as “sealer” coats or “finish” coats.

Only topcoats approved by International Protective Coatings should be applied over Interchar products. A list of the approved topcoats can be found on the latest version of the Technical Data Sheet. International Protective Coatings can advise on other suitable topcoats.

Prior to the application of the topcoat, the applicator must ensure that the specified dry film thickness of Interchar product has been achieved. Interchar 1120 should be allowed to harden sufficiently so that accurate thickness readings can be taken.

The surface of the Interchar 1120 must be clean, dry and free from contamination before overcoating with the topcoat. The topcoat must be applied within the overcoating intervals specified. Consult the Interchar 1120 product data sheet for specific details.

Depending on the choice of topcoat colour, two or more coats may be necessary to achieve full opacity. The dry film thickness of topcoat required to give a uniform finish will also be influenced by the unevenness of the surface of the Interchar 1120. It should be noted that the quality of surface finish is entirely dependent on the final surface appearance of the Interchar product; topcoats will tend to highlight rather than hide uneven texture. It is important that the Interchar is applied and finished to the required quality prior to application of any topcoat (see section 10 for further information).

Where Interchar products are to be subjected to environmental conditions other than C1 (as defined in ISO 12944-2) then a topcoat **MUST** be applied. Even when the Interchar system is correctly topcoated, any contact with ponding or standing water must be avoided.

The minimum overcoating interval for Interchar 1120 with all topcoats is 24 hours.

ID 1120wp_uk	Rev. 01	Date 30/07/09	Interchar 1120	Page 10 of 18
-----------------	------------	------------------	----------------	---------------

8.0 Airless Spray Application

Power stirring is essential to ensure that the coating is mixed to a uniform consistency. Hand held air driven mixers are the most common and are ideal for this purpose, preferably with a helical style shaft. Material should not be stirred excessively, due to the risk of incorporating excessive air.

Manual mixing (e.g. using a palette knife) is not recommended.

Airless spray pumps capable of achieving a minimum pressure at the tip of 2500psi (175kg/cm²) are recommended. Electrically driven airless pumps capable of achieving the above parameters have also been found to be suitable.

For air driven airless spray pumps the following modifications to the normal set up are recommended:

- Remove any wet end extension hose and place the wet end directly into the coating.
- Place the pail or drum so that condensation from the pump does not run into the coating.
- The pump should be fitted with a filter to prevent contamination from external sources from entering the spray machine and causing blockages.
- Use the minimum length of 9mm (0.35 inch) bore fluid line. A 2 metre (6.5 feet), 6.5mm (0.26 inch) bore whip end with a swivel connection to the spray gun makes the fluid lines much easier to handle and more manoeuvrable.
- Maximum hose length 60m (~200 feet); increased pressure may be required.

The recommended airless spray tip range is 17 – 21 thou. (0.43 – 0.54mm)

Interchar 1120 is supplied ready for use and thinning is not recommended.

Multiple Coat Application

Where the specified dry film thickness of Interchar 1120 is greater than 700 microns (28 mils), the total thickness should be built up in two or more applications up to a maximum wet film thickness of 1000 microns per coat, using the recommended overcoating windows from the technical datasheet. Prior to overcoating ensure the previous coat is dry. Particular attention should be paid to the internal angles of flanges and webs where excessive build up of paint can occur and air flow may be restricted. Excessive paint application in these areas can be removed by simply running a small paint brush down the internal angles whilst the paint is wet.

Drying can be optimized by maintaining air temperatures above 10°C by improving air flow, particularly in areas where natural air flow is restricted and by keeping relative air humidity as low as possible. Drying times will be optimized if successive coats are of similar thickness. For further advice on overcoating intervals contact International Protective Coatings.

During application it is important that the applied wet film thickness is continually monitored to ensure the required thickness is being applied. Good control of thickness per coat will facilitate more rapid job completion.

ID 1120wp_uk	Rev. 01	Date 30/07/09	Interchar 1120	Page 11 of 18
-----------------	------------	------------------	----------------	---------------

9.0 Brush & Roller Application

Application of Interchar 1120 by brush or roller is a suitable method but is generally recommended for small areas and repairs only.

Between 250-400microns (10-16mils) wet film thickness can be achieved per coat. For a typical dry film thicknesses required for 2 hour fire protection, multiple coats applied by brush or roller will be required.

The appearance of brush or roller applied Interchar 1120 will be different to that of the spray applied coating, which will provide the smoothest finish.

ID 1120wp_uk	Rev. 01	Date 30/07/09	Interchar 1120	Page 12 of 18
-----------------	------------	------------------	----------------	---------------

10.0 Standard Of Cosmetic Finish

The cosmetic finish of Interchar 1120 will vary depending on the method of application. Spray application of the coating is generally considered to give a superior appearance to brush application.

Particular requirements for the quality of the finish should be stated in the specification. For non-visible areas, for example, the standard of finish achieved may not be of concern.

At the outset of a project it is strongly recommended that a sample area is prepared and the standard of cosmetic finish is agreed by all parties concerned.

SCI P160 Part 2 section 4.3 clause R470 outlines three standards which can be specified:

i) Basic Finish

The coating system achieves the required fire performance and corrosion protection performance but is not required to achieve any requirement for standard of finish.

ii) Decorative Finish

In addition to the requirements for (i) above, a good standard of cosmetic finish is generally required when viewed from a distance of 5 metres. Minor "orange peel" or other texture resulting from application or localised repair is acceptable.

iii) Bespoke Finish

In addition to the requirements for (i) above, the coating finish is required to have a standard of evenness, smoothness and gloss agreed between the Specifier and Contractor.

More work will be required to achieve the higher standards. It may be necessary to abrade the Interchar 1120 surface to remove texture. It may also be necessary to apply the Interchar 1120 in a series of thinner coats.

Topcoats are relatively thin and will tend to highlight rather than hide surface defects. It is, therefore, important to ensure that the required finish has been achieved prior to application of the topcoat.

ID 1120wp_uk	Rev. 01	Date 30/07/09	Interchar 1120	Page 13 of 18
-----------------	------------	------------------	----------------	---------------

11.0 Possible Film Defects

A number of potential defects are detailed below together with recommended remedial treatment.

Over-Application

Excessive film thickness will lead to extended drying and may lead to other surface defects. This will be more apparent in areas such as corners and internal angles of universal sections and may result in hairline cracking in these areas. This cracking is not detrimental to the integrity or fire performance of the Interchar 1120. To eliminate these effects, caution should be exercised when coating narrow-webbed sections. If necessary to control the film thickness in these areas the applied wet film thickness per coat should be reduced from the 1000 microns maximum

Overspray / Dry Spray

Any dry overspray of Interchar 1120 onto adjacent primed steelwork should be removed from the surface prior to application of the Interchar 1120. Failure to do so may impair adhesion and affect final appearance.

Overspray present on Interchar 1120 may give a rough appearance to the surface. Sometimes this can be dusted off but abrasion may be required to achieve a satisfactory smooth finish onto which a topcoat can be applied in order to satisfy the requirements for cosmetic appearance.

Overspray can be minimised by good work planning and good spray technique such as reduction of air pressure, sensible tip size, etc, depending on the structure to be sprayed. The sprayer should be close enough to the work surface at all times to minimise airborne overspray without leading to excessive ripples or other texture in the coating caused by the pressure of the spray. All dry overspray must be removed prior to topcoating Interchar 1120.

For large areas or areas where overspray may be unavoidable, it is advised that the adjacent steelwork be covered or taped to prevent overspray damaging cosmetic appearance.

Overspray will have the appearance of a non-closed film and/or surface roughness.

Sagging

The result of excessive film thickness and poor spray technique or over-thinning. Any areas which are subject to this should have the coating removed and re-applied.

Protective Coatings

All products supplied and technical advice or recommendations given are subject to our standard Conditions of Sale.

Registered in England No. 63604
Registered Office 26th Floor, Portland House, Bressenden Place, London SW1E 5BG

ID 1120wp_uk	Rev. 01	Date 30/07/09	Interchar 1120	Page 14 of 18
-----------------	------------	------------------	----------------	---------------

13.0 Measurement Of Dry Film Thickness

After sufficient drying time a survey of the dry film thickness should be carried out using a suitable calibrated gauge. An electromagnetic induction instrument with a statistical function to store readings and give an average is most useful. Where dry film readings include a primer and/ or top coat an allowance must be made for these coatings and subtracted from the total reading.

The following is the recommended procedure for measuring dry film thickness and acceptance criteria based on Section 5.4 Testing, Clause R630 of SCI P160, part 2. Readings should be taken on every steel section as follows:

I sections

Webs: Two readings per metre length on each face
Outer flanges: Two readings per metre length on each face
Inner flanges: One reading per metre length on each face

Hollow sections:

Eight readings per metre length spread evenly around the section.

No readings should be taken within 25mm of any edge or web/flange junction.

Indicative dry film thickness readings can be taken on Interchar products which have not fully hardened. This can be achieved by taking the readings over a shim using the following simple steps;

- Place a rigid shim of known thickness on the Interchar surface
- Take readings over the shim.
- Subtract the thickness of the shim, and the primer and topcoat if applied, to give the dry film thickness of Interchar product.

This will give an indication only of the dry film thickness of the Interchar material.

Dry Film Thickness Acceptance Criteria

The average thickness of each steel section should be equal to, or greater than, the specified thickness. Where any single thickness reading is found to be less than 80% of the specified thickness, a further three readings should be taken on the same face within a 300mm radius of the low reading.

If one or more of the additional readings are also less than 80% of the specified thickness, further readings should be taken to establish the extent of the area of under thickness and the whole area should be brought up to the specified thickness.

Individual thickness readings of less than 50% of the specified thickness are not acceptable.

The average measured dry film thickness of any steel section should not exceed by more than 10% of the maximum stated dry film thickness for the particular steel shape and orientation (as quoted in the latest published loading tables for the specific Interchar product).

Protective Coatings



All products supplied and technical advice or recommendations given are subject to our standard Conditions of Sale.

Registered in England No. 63604
Registered Office 26th Floor, Portland House, Bressenden Place, London SW1E 5BG

ID 1120wp_uk	Rev. 01	Date 30/07/09	Interchar 1120	Page 15 of 18
-----------------	------------	------------------	----------------	---------------

Other measuring schedules and acceptance criteria are in use, for example the AWCI (Association of Wall and Ceiling Industries) Technical Manual 12-B.

Correction Procedure

Where the dry film thickness is found to be unacceptable because it is less than that required by the specification, remedial action will be necessary.

The applicator must first establish the extent of the low thickness. Areas of low thickness may be random but frequently a pattern can be observed e.g. low thickness tending to occur on inner flanges. Additional material should be applied to ensure conformance with the dry film thickness acceptance criteria stated above

The surface of the existing Interchar coating must be clean, dry and free from all contamination. If the topcoat has already been applied it will need to be removed.

Where the dry film thickness exceeds the recommended limit, guidance should be sought from International Protective Coatings.

Dry Film Thickness of the Topcoat

The top coat dry film thickness is difficult to measure due to the variation in thickness of the underlying coats of intumescent and its own relatively low thickness in comparison.

It is, however, important that the topcoat is applied at the specified thickness to ensure the longevity of the system without applying excessive thickness. Judging the thickness of the top coat is also made more difficult as an uneven surface will require more coating to achieve a uniform appearance. As a guide, the number of spray gun passes to achieve the required wet film thickness can be determined by spraying on to a smooth surface. Monitoring of material usage will also give an indication of the applied thickness.

Protective Coatings

All products supplied and technical advice or recommendations given are subject to our standard Conditions of Sale.

Registered in England No. 63604
Registered Office 26th Floor, Portland House, Bressenden Place, London SW1E 5BG



ID 1120wp_uk	Rev. 01	Date 30/07/09	Interchar 1120	Page 16 of 18
-----------------	------------	------------------	----------------	---------------

14.0 Inspection And Repair

The repair method will depend upon the extent of the damage. Repairs should be carried out at the earliest opportunity using the appropriate procedure from those given below.

Damage Down to Steel

Remove unsound and damaged coatings to a neat firm edge with sound adhesion. Remove all corrosion products. For limited small areas prepare steel surface in accordance with SSPC SP11 without polishing the substrate. For large areas of repair the exposed steel surface should be prepared by abrasive blasting to a minimum standard of Sa2½ (ISO 8501-1:2007) or SSPC-SP6.

Feather coat edges by abrading. Reinststate the original or other priming system recommended by International Paint. Avoid overlap of primer onto surrounding Interchar 1120. Reinststate the Interchar 1120 within the recommended overcoating limits of the repair primer.

Apply Interchar 1120 in multiple applications by brush. If a topcoat has already been applied to the existing system, minimise overlap of fresh Interchar product over the existing topcoat. Apply topcoat as appropriate.

Damage Not Requiring Primer Repair

Depending on severity of damage, either lightly abrade the damaged area to a feathered edge, or cut out a suitable area of Interchar 1120 and feather out the edges. If cutting out, do not damage the priming system, otherwise repair as for damage down to steel will be required.

Reinststate Interchar 1120 to the required dry film thickness using the method described above. After the appropriate overcoating interval apply an approved topcoat in accordance with original specification.

Hairline cracks are not detrimental to the integrity or fire performance of the Interchar 1120. Where they do occur repairs can be carried out by application of a brush coat of Interchar 1120 or a stripe coat of topcoat followed by a full coat of the topcoat

Damage to Topcoat Only

Remove loose or unsound coatings to a firm edge and feather the edges. All surfaces should be clean, dry and free from all contamination.

Reinststate top coat in accordance with original specification.

Protective Coatings

All products supplied and technical advice or recommendations given are subject to our standard Conditions of Sale.

Registered in England No. 63604
Registered Office 26th Floor, Portland House, Bressenden Place, London SW1E 5BG



ID 1120wp_uk	Rev. 01	Date 30/07/09	Interchar 1120	Page 17 of 18
-----------------	------------	------------------	----------------	---------------

Future Inspection and Maintenance

The fire protection properties of the Interchar systems will remain as long as the integrity of the coating is maintained. Regular inspections of the Interchar fire protection system should be carried out. Any defects, damaged areas etc. must be repaired as recommended above.

The inspection intervals for a project should be stated in the specification. Typically, inspections should be carried out annually.

Topcoats must be maintained as a continuous film to protect all Interchar products from the environment. However, excessive build up of top coat thickness could be detrimental to the fire protection system and must be avoided. As a guide the maximum recommended number of topcoats is two, applied at 50 microns DFT per coat.

Only approved topcoats can be applied over all Interchar products. For further information contact International Protective Coatings.

Protective Coatings

All products supplied and technical advice or recommendations given are subject to our standard Conditions of Sale.

Registered in England No. 63604
Registered Office 26th Floor, Portland House, Bressenden Place, London SW1E 5BG




ID 1120wp_uk	Rev. 01	Date 30/07/09	Interchar 1120	Page 18 of 18
-----------------	------------	------------------	----------------	---------------

15.0 Health & Safety

Interchar 1120 is intended for use only by professional applicators in industrial situations in accordance with the advice given in this document and on containers and should not be used without reference to the Material Health and Safety Data Sheets (MSDS) which International Protective Coatings has provided to its customers. If for any reason a copy of the relevant Material Health and Safety Data Sheet is not immediately available, the user should obtain a copy before using the product.

- Ensure that all typical personal protective equipment is used, e.g. overalls, gloves, goggles, face mask, barrier creams etc.
- Provide adequate ventilation.
- If product comes into contact with the skin wash thoroughly with lukewarm water and soap or suitable industrial cleaner. Do not wash with solvents. If the eyes are contaminated, flush with water (minimum 10 minutes) and obtain medical attention at once.
- Observe all precautionary notices on containers.

TECHNICAL AND APPLICATION DATA herein is for the purpose of establishing a general guideline of the coating and proper coating application procedure. Test performance results were obtained in a controlled laboratory environment and International makes no representation that the exhibited published test results, or any other tests, accurately represent results actually found in all field environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection, verification of performance, and use of the coating(s).

 , International and all product names mentioned in this publication are trademarks of, or licensed to, Akzo Nobel.

Protective Coatings

All products supplied and technical advice or recommendations given are subject to our standard Conditions of Sale.

Registered in England No. 63604
Registered Office 26th Floor, Portland House, Bressenden Place, London SW1E 5BG

