

BerryAlloc Dhr. Geert Hoet Industrielaan 100 8930 MENEN



Your notice of

Your reference

Date

08-05-2012

08-06-2012

Analysis Report 12.01991.02

Translation of analysis report 12.01991.01, made on 08-06-2012

Required tests:

EN 13501-1 (2007) + A1 (2009)

Identification Information given by the client number		Date of receipt		
T1206167	PURELOC	08-05-2012		

Petra Wittevrongel

Order responsible

This report runs to 7 pages and may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.

The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples. In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

VAT BE 0459.218.289

Fin. Acc. 210-0472965-45

IBAN BE44 2100 4729 6545

CENTEXBEL-GENT
Technologiepark 7
BE-9052 Zwijnaarde
Tel. + 32 9 220 41 51 • Fax + 32 9 220 49 55
gent@centexbel.be

CENTEXBEL-VERVIERS
Avenue du Parc 38
BE-4650 Herve (Chaineux)
Tel. + 32 87 32 24 30 Fax + 32 87 34 05 18
chaineux@centexbel.be



Date 08-06-2012

Page 2/7

Reference:

T1206167 - PURELOC

# Information given by the client

Product standard

EN 13501-1 (2007) + A1 (2009)

Floor covering type

Homogeneous and heterogeneous polyvinyl chloride floor

coverings

EN product standard

EN 649

Mass

6.6 kg/m<sup>2</sup>

Thickness

4.0 mm

Notified body No: 0493



Date 08-06-2012

Page 3/7

Reference:

T1206167 - PURELOC

<u>Reaction to fire tests – Ignitability of building products subjected to direct impingement of flame - Single-flame source test</u>

Date of ending the test

29-05-2012

Standard used

EN ISO 11925-2 (2010)

Product standard

EN 13501-1 (2007) + A1 (2009)

Floor covering

Deviation from the standard

Conditioning

23°C, relative humidity 50%

Minimum 14 days or until constant mass is achieved

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Substrate

Fibre cement board - density (1800  $\pm$  200) kg/m<sup>3</sup>

Mounting

Loose-laid

Cleaning

Specimens have not been cleaned



Date 08-06-2012

Page 4/7

Flame application time (s)

15

Flame application

Surface

	Length			Width		
	1	2	3	4	5	- 6
Time to reach 150 mm mark (s)	*	*	*	*	*	*

<sup>\* =</sup> time to reach the mark > 20 s

Criteria Floorcoverings

time to reach the mark:

- ≥20 s : Class Efl

- < 20 s : Class Ffl

Classification

Class En

Limitations

This classification document does not represent type approval or certification of the product.



Date 08-06-2012

5/7 Page

Reference:

T1206167 - PURELOC

# Reaction to fire tests for floorings - Determination of the burning behaviour using a radiant heat source

Date of ending the test

06-06-2012

Standard used

EN ISO 9239-1 (2010)

Product standard

EN 13501-1 (2007) + A1 (2009)

Deviation from the standard

Conditioning

23°C, relative humidity 50%

Minimum 14 days or until constant mass is achieved

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

#### Test specimen

Substrate

Fibre cement board - density (1800  $\pm$  200) kg/m<sup>3</sup>

Mounting

Loose-laid

Cleaning

Specimens have not been cleaned

Joint

In length direction: in the middle

In width direction: each 17.1 cm



Date 08-06-2012

Page 6/7

### Radiant heat flux

	Flame spread distance (cm)			Flame time	Heat flux *	
	10 min	20 min	30 min		kW/m²	
Length						
#1	<11	<11	<11	12 min 10 s	≥ 11.0	
Width						
#1	11	11	11	12 min 05 s	10.4	
#2	11	11	11	12 min 05 s	10.4	
#3	12	12	12	12 min 25 s	10.3	
Average					10.4	

<sup>\*</sup> Heat flux at the time of flame extinguishment or after a test duration of 30 minutes.

Fire cla	assification in accordance with EN 13501	-1 (2007) + A1 (2009)	
Class	EN ISO 11925-2 or CWFT	EN ISO 9239-1 (test duration = 30 min)	
B <sub>fl</sub>	En	heat flux ≥ 8,0 kW/m <sup>2</sup>	
Cfl	E <sub>fl</sub>	heat flux $\geq 4.5 \text{ kW/m}^2$	
D <sub>fl</sub>	E <sub>fl</sub>	heat flux $\geq 3.0 \text{ kW/m}^2$	

Smoke production: Light attenuation

	Maximum (%)	Total (%.min)
Length		
#1 23		139
Width		
#1	25	164
#2	23	117
#3	24	162
Average		148

Additional classification in accordance with EN 13501-1 (2007) + A1 (2009)			
smoke production ≤ 750%.min	s1		
smoke production > 750%.min	s2		



Date 08-06-2012

Page 7/7

## Reaction to fire classification: Bn/s1

loose-laid on a non-combustible substrate\*

\* End use substrates of classes A1or A2-s1,d0 (ISO 13238:2010 § 5.2.2)

#### Limitations

This classification document does not represent type approval or certification of the product. "The classification assigned to the product in this report is appropriate to a declaration of conformity by the manufacturer within the context of system 3 attestation of conformity and CE marking under the Construction Products Directive.

The manufacturer has made a declaration, which is held on file. This confirms that the products design requires no specific processes, procedures or stages (e.g. no addition of flame -retardants, limitation of organic content, or addition of fillers) that are aimed at enhancing the fire performance in order to obtain the classification achieved. As a consequence the manufacturer has concluded that system 3 attestation is appropriate.

The test laboratory has, therefore, played no part in sampling the product for the test, although it holds appropriate references, supplied by the manufacturer, to provide for traceability of the samples tested."